

RAW MATERIAL DATA SHEET

ACTIVATED CARBON AC 20

PHISICALLY ACTIVATED CARBON ORIGINATED BY MINERAL EXTRUSION.

TYPICAL ANALYSIS	UNIT OF MEAS.	VALUE	METHOD
APPARENT DENSITY	KG/MC	600 ± 60	ASTM 2854-89
DIAMETER	MM	4	
HUMIDITY	%	2 MAX	ASTM 2867-88
ABRASION RESISTANCE	%	8 MIN	ASTM 3802-89
SURFACE AREA	MG/G	600 MIN	BET CON AZOTO
CCI <sub>4</sub> ADSORPTION	%	35 MIN	ASTM 3467-89
IGNITION TEMPERATURE	°C	480 MAX	ASTM 3466-88
PRESSURE DROP AT 0.3 M/S	MM H <sub>2</sub> O/M	130	
PRESSURE DROP AT 0.4 M/S	MM H <sub>2</sub> O/M	180	

THE INFORMATION IN THESE TECHNICAL SHEET ARE BASED ON ANALYSIS OF MATERIAL SUPPLIED SO FAR.  
THEY ARE NOT BINDING.

RESETT ENGINEERING SRL

SEDE LEGALE VIA BALBO, 35 60044 FABRIANO AN  
STAB./ AMM. VIA PIANI DI MARISCHIO 38 60044 FABRIANO AN  
TEL. 0039 0732 73551 FAX 0039 0732 73473  
P. IVA 02220740423 CAP. soc. € 10.000,00