

RAW MATERIAL DATA SHEET

CARBOTEX 220 10

PROPERTY	STANDARD	UNIT	VALORE MD/CD
MASS PER UNIT AREA	EN29073-1	G/MQ	220 ± 22
THICKNESS	ENISO 9073-2 METHOD A	MM	9 ± 2
AIR-PERMEABILITY ¹	ENISO 9237	I/M ² /s	1500/300
FLAMMABILITY	DIN 53 438, PART 3		F1
COLOUR	BLACK		
FIBRE COMPOSITION	POLYESTER		
FIBRE BONDING	THERMO BONDED		
TREATMENT	IMPREGNATED		

MD: MACHINE DIRECTION

CD: CROSS DIRECTION

¹
MEASURED AT 50 PA

MAX. WIDTH IS 2000MM
TOLERANCE OF WIDTH IS: ±20MM

LABORATORY TESTS ARE CARRIED OUT ON NON-CONDITIONED SAMPLES IN NON-CONDITIONED TESTING ENVIRONMENT. TESTING CONDITIONS DO NOT INFLUENCE THE RESULTS ACCURACY.

RESETT ENGINEERING SRL

SEDE LEGALE VIA BALBO, 35 60044 FABRIANO AN
STAB./ AMM. VIA PIANI DI MARISCHIO 38 60044 FABRIANO AN
TEL. 0039 0732 73551 FAX 0039 0732 73473
P. IVA 02220740423 CAP. soc. € 10.000,00