

RAW MATERIAL DATA SHEET

ACTIVATED CARBON AB (NRC 55)

PHYSICALLY ACTIVATED CARBON ORIGINATED BY MINERAL EXTRUSION.

TYPICAL ANALYSIS	UNIT OF MEAS.	VALUE	METHOD
APPARENT DENSITY	Kg/Mc	670-700	ASTM2854-89
DIAMETER	MM	4	
HUMIDITY	%	15MAX	ASTM2867-88
ABRASION RESISTANCE	%	98MIN	ASTM3802-89
SURFACE AREA	Mq/g	950MIN	BET CON AZOTO
CCI4 INDEX	%	45MIN	ASTM3467-89



RESETT[®]
engineering^{srl}

THE INFORMATION IN THESE TECHNICAL SHEET ARE BASED ON ANALYSIS OF MATERIAL SUPPLIED SO FAR.
THEY ARE NOT BINDING.

RESETT ENGINEERING SRL

SEDE LEGALE VIA BALBO, 35 60044 FABRIANO AN
STAB./ AMM. VIA PIANI DI MARISCHIO 38 60044 FABRIANO AN
TEL. 0039 0732 73551 FAX 0039 0732 73473
P. IVA 02220740423 CAP. soc. € 10.000,00