

RAW MATERIAL DATA SHEET

NATURAL ZEOLITE

PHYSICAL PROPERTIES	UNIT OF MEAS.	VALUE	METHOD
APPARENT DENSITY	kg/mc	850 ± 20	ASTM 2854-89
DIAMETER OF SPHERES	m/m	2.5	
HUMIDITY	%	7 Max	ASTM 2867-88
ABRASION RESISTANCE	%	90 min	ASTM 3802-89
ACID-BASIC STABILITY RANGE		4-8 Ph	
C.E.C FOR AMMONIUM ION (NH ₄)		195 meq/ 100g	
POINT OF IGNITION	°C	400 Max	ASTM 3466-88
AIR SPEED	PRESSURE DROP	Ø 2.5MM	
PRESSURE DROP AT 0.2 M/S	KPA/M	1.7	
PRESSURE DROP AT 0.3 M/S	KPA/M	2.8	
PRESSURE DTOP AT 0.4 M/S	KPA/M	4.5	

RESETT ENGINEERING SRL

Sede legale Via Balbo, 35 60044 Fabriano AN
 Stab./Amm. Via Piani di Marischio 38 60044 Fabriano AN
 Tel. 0039 0732 73551 Fax 0039 0732 73473
 P. Iva 02220740423 Cap. soc. € 10.000,00